

## CP 200 PERFORMANCE GRADE, MEDIUM-HIGH ADHESION MASKING TAPE

### TYPICAL APPLICATIONS

- For moderate temperature paint masking and metal fabrication applications in the transportation (auto, coaches and buses) industry

### PRODUCT FEATURES

- More conformable around curved surfaces than most other automotive masking tapes
- Instant, medium-high adhesion to various automotive surfaces (metal, rubber, plastic, anodized aluminum and chrome)
- Resistant to water, various solvents and oil
- Compatible with solvent-based and waterborne paints and coatings for automotive and industrial applications
- Good for tape on tape applications (shingling)
- Clean removal
- Heat-resistant tape withstands bake cycles up to 200 F (for up to 30 minutes)
- UV-resistant for up to 3 days in outdoor environments

### CONSTRUCTION

Backing: Crepe paper

Adhesive: Rubber-based adhesive

### STANDARD WIDTHS

0.7 in; 0.94 in; 1.41 in; 1.88 in  
18 mm; 24 mm; 36 mm; 48 mm

### STANDARD LENGTH

60.1 yd  
55 m

Lead times may apply. Please contact Shurtape customer service for information related to stock and non-stock sizes and colors.

### STANDARD CORE SIZE

3 in

### APPLICABLE STANDARDS

ASTM D 6123/D 6123M-97 (2012), Type I

### STORAGE & USAGE CONDITIONS

Tape should be stored in its original packaging in a cool, dry area away from direct sunlight and should be used within 12 months of date of shipment. Surfaces to which tape is applied should be clean, dry and free of grease, oil or other contaminants.

### COLOR



### PHYSICAL PROPERTIES

	STANDARD	METRIC
Adhesion to Stainless Steel	39 oz/in width	4.27 N/10 mm
Elongation	9%	9%
Service Temperature Range	60 F to 200 F	15 C to 93 C
Tensile	24 lbs/in width	42.0 N/10 mm
Thickness	6.1 mils	0.15 mm

Physical and performance characteristics shown above are obtained from tests recommended by PSTC, ASTM, government agencies or Shurtape Technologies, LLC, Quality Assurance and Technical Service departments and do not represent a guarantee of product performance. Individual rolls may vary slightly from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.

